



**Gellner Industrial, LLC**  
**105 Tide Road, Hometown, PA 18252**  
**PHONE: 570-668-8800**  
**www.gellnerindustrial.com**  
*water based industrial polymers*



## **Ottopol 523 Technical Data sheet**

---

### ***Product Overview***

#### **HYDROXYL FUNCTIONAL ACRYLIC**

Ottopol 523 is an anionic hydroxyl functional acrylic emulsion. The functionality allows the polymer to cross-link with melamine or aziridine. The use of aziridine will result in a short pot life and will cross-link at room temperature. Formulations using aziridine will require a plasticizer or coalescent solvent to aid the film formation of the dried coating. Formulations using melamine and PTSA (Para-Toluene Sulfonic Acid) are stable for a minimum of thirty days. The starting formulation requires a web temperature of 180 degrees Fahrenheit to activate cross-linking of the resins. An increase in PTSA will lower the temperature required to activate cross-linking. Larger amounts of PTSA will increase the hardness of the dry film. There are no plasticizers or coalescent aids required for film formation when using a melamine resin with Ottopol 523.

#### **HIGH BLOCKING**

Catalyzed coatings inherently have high blocking properties, when compared to systems that are not cross-linked.

#### **RESISTANCE PROPERTIES**

**MEK ----- 200+ Rubs**  
**Water -----24+ Hours**  
**Isopropyl Alcohol ----- 200+ Rubs**  
**Household Cleaners ----- 200+ Rubs**  
**Stain Resistance -----Dyes in Food**

The cured coating has excellent resistance to many solvents and liquids. The stain resistance is excellent. Food and foods containing dyes can completely dry on the surface without staining. Removal of the dried substance requires little effort. It usually peels or scratches off the coating, requiring no cleaners or scrubbing.

<b>Product</b>	<b>Specifications</b>
Description..... Acrylic Emulsion	Specific Gravity..... 1.0598
Appearance ..... Milky White	Freeze Thaw Stability .....None
Solids ..... 44.0 - 46.0%	Glass Transition Temperature ..... 105
pH .....6.5 – 7.5	FDA Status ..... 176.180
Viscosity.....500 - 1500 cps	USDA Approved .....No
Weight / Gallon ..... 8.84 lb.	

**Ottopol Starting Formulations: Stable Catalyzed Varnish**

<b>Product Code</b>	<b>Amount</b>
1) Ottopol 523-----	150.0
2) Cyanamid Cymel 303 (Melamine)* ---	11.0
3) Water-----	10.0
4) Cyanamid Cycat 40:40 (PTSA 40%)* ---	3.5
5) Aqua Ammonia 28% -----	<u>0.5</u>
	175.0

*Place component 1 & 2 in a container with agitation and allow to mix for 10 minutes. Pre-mix components 3, 4, & 5 in a suitable container for several minutes. There will be a mild exothermic reaction.. Some water must be included in this step to prevent precipitation between the acid and amine. Pour the pre-mixture into the container and allow to mix for 10 minutes.*

*Viscosity 200 - 500 cps*

**Ottopol Starting Formulation: 50% Crosslinked with Polyisocyanate**

<b>Product Code</b>	<b>Amount</b>	<b>Viscosity</b>
1) Ottopol 523	100.0	200-500 cps
2) Water	10.0	
3) Texanol	10.0	440 cps
<b>Step A:</b> Mix components 1, 2 & 3 for 10 minutes		
4) Bayer Corp. Bayhydur XP-7063**	4.2	430 cps

**Step B:** Add component 4 and mix compound for 30 minutes

**Cyanamid\* -----1-800-438-5615**  
**Bayer Corp. Bayhydur XP-7063\*\* -----1-412-777-2000**

All product information contained in our product literature as well as any suggestions for use of our products contained in that literature, is based on information we believe to be reliable. However since particular conditions and methods of use involved in a particular product application are beyond our control, any such information is to be regarded as merely suggestive and should be verified by each user. Any suggestion made regarding the use of our products should not be construed as any authorization to infringe on patents, trademarks or similar rights of others.

Gellner Industrial, LLC., warrants that its products have been manufactured with due care, are free of defects in material or workmanship, and conform to the specifications stated in the data sheets applicable to each product or to specifications otherwise explicitly agreed upon in a writing which refers to this warranty. THIS WARRANTY IS IN LIEU OF ANY OTHER EXPRESS OR IMPLIED WARRANTIES, INCLUDING WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE. Gellner Industrial, LLC.'s liability under this warranty is limited to replacing, free of charge, any product that is found upon examination by Gellner Industrial, LLC., to be defective. Gellner Industrial, LLC., SPECIFICALLY DISCLAIMS ANY LIABILITY FOR CONSEQUENTIAL DAMAGES. It is strongly recommended that a prospective user of one of our products verify the suitability of that product for a given application before its use in production.