



Gellner Industrial, LLC

105 Tide Road, Hometown, PA 18252

PHONE: 570-668-8800

www.gellnerindustrial.com

water based industrial polymers



Ottopol KXO-68 Technical Data Sheet - Reference Number 300-202-68

PRODUCT SPECIFICATIONS

Description ----- 100% Acrylic Emulsion
Solids ----- 39.0 - 41.0%
pH ----- 4.5 – 5.5
Viscosity ----- 500 cps Max
Flash Point ----- Same as Water
Glass Transition Temp. ----- 23 Degrees C

Appearance ----- Translucent Emulsion
Specific Gravity ----- 1.0548
Weight/Gallon ----- 8.80
Freeze Thaw Stability - Keep from Freezing
Charge ----- Positive Cationic
MFFT ----- <1 Degree Celsius

AMBIENT CURE

Inks and coatings made from Ottopol KXO-68 that are cured without elevated temperatures and only relying on room temperature curing will result in a dry film that has excellent water resistance in a few hours and has chemical and alkali resistance in less than 24 hours. Elevated temperature will accelerate the resistance properties.

ALKALI RESISTANCE

After a 24 hour ambient cure, the dry film will have alkali resistance to a 4% caustic solution, when soaked for 15 minutes at 110 degrees Fahrenheit.

SOLVENT RESISTANCE

After less than 24 hours ambient cure, films that are 1.75 mils wet thickness had over 20 rubs Isopropyl Alcohol resistance.

ADHESION TO SUBSTRATES

The positive charge allows inks and coatings to have exceptionally good adhesion to plastic films: Mylar, PVC, PET and polystyrene. Adhesion to foil and other metallic surfaces is excellent.

Ottopol KXO-68 Polymer's Attributes

- ✓ **Blocks Tannin Oils:** Tannin oils from wood, such as redwood, red cedar and other species are easily blocked with *Ottopol KXO-68*.
- ✓ **Blocks Stains on Drywall:** Hard to block washable markers are effortlessly blocked, as well as other types of markers including felt tip markers. Lipstick and Vaseline will also be blocked with this polymer.
- ✓ **Meets Visual Assessment for ASTM Standard D7514-14:** Evaluating Ink Stain Blocking of Architectural Paint Systems.
- ✓ **Blocks Water Stains from Concrete Blocks in Basements:** Damp basements are a common problem, particularly here in the United States. *Ottopol KXO-68* forms a water proof barrier under these wet conditions, eliminating unsightly stains on basement walls.
- ✓ **Blocks Fungal Growth in Damp or Humid Environments:** High humidity environments cause the growth of mildew. The cationic nature of *Ottopol KXO-68* forms natural barrier of the growth of fungi.
- ✓ **Excellent Adhesion:** *Ottopol KXO-68* and products made from this polymer display excellent adhesion to a variety of surfaces.

Primer and Polymer Attributes: 1.75 mil wet film thickness

- 1) 3 Hour Ambient Cure followed by 24 Hour Water Submergent Test.
Substrate was an aluminum Q-Panel. After 3 hours curing at ambient temperature the panel was placed in water for 24 hours. There were no signs of blushing, blistering or delamination. Minimal softening was observed using the fingernail test, which quickly recovered in less than 5 minutes.

Primer and Polymer Attributes: 1.75 mil and 3 mil wet film thickness

- 2) 24 Hour Ambient Cure followed by 24 Hour Water Submergent Test
Substrate was aluminum Q-Panel. After 24 hours curing at ambient temperature the panel was placed in water for 24 hours. There were no signs of blushing, blistering or delamination. Minimal softening was observed using the fingernail test, which quickly recovered in less than 5 minutes.

Self-Healing Polymer

- 3) If the coating or primer is stressed beyond these guidelines and blisters, it becomes a self-healing coating recovering within a matter of minutes.

STARTING POINT FORMULA

Reference Number 600-258-7E

For DIY Primer with Stain-Blocking and Water-Proofing Characteristics

Part "A" Grind – 74.3% Solids Dispersion before component #7 for dilution

1) Water -----	102.30
2) Ottosperse -----	6.80
3) Acetic Acid 99% -----	6.80
4) BYK 022 -----	2.10
5) Micral 932 -----	170.60
6) Kronos TiO2 2310-----	170.60
7) Water -----	<u>37.50</u>
Grind Total-----	496.70

Dispersing Aid from Gellner Industrial, LLC
pH Adjustment from Brenntag
Defoamer from BYK
Filler from Huber
TiO2 from Kronos

Part "B" Letdown

8) Ottopol KXO-68-----	492.20
9) BYK 022 -----	2.10
10) BYK 3450-----	2.30
11) RHEOBYK H6500VF-----	<u>6.70</u>
Total Primer Weight -----	1,000.00

Cationic Emulsion from Gellner
Defoamer from BYK
Wetting Agent from BYK
Rheology Modifier from BYK

Procedure:

- 1) Weigh Water (1) in the Mixing Vessel and Start Agitation.
- 2) Add Ottosperse (2), Acetic Acid (3) and BYK 022 (4) While Mixing and Let it Mix for 5 Minutes.
- 3) Under High Shear add Micral 932 (5), Followed by TiO2 (6) Slowly.
- 4) Shear Until Desired Grind is Achieved on a Grind Gauge, 15 - 20 minutes.
- 5) Add Water to Dilute and Lower the Viscosity. Let Mix for 5 minutes.
- 6) In a Separate Container, Weigh Out the *Ottopol KXO-68* (8), Then Add BYK-022 (9) Followed by BYK-3450 (10) While Maintaining Good Agitation.
- 7) Let Mix for 5 Minutes.
- 8) Add the Grind to Letdown and Let it Mix for 10 Minutes.
- 9) Finally, Add RHEOBYK-H6500VF (11) Under Moderate Agitation.

Primer Specification:

Solids -----	54 - 56%
pH-----	4.00 - 6.00
Viscosity-----	95 - 100 KU

All product information contained in our product literature as well as any suggestions for use of our products contained in that literature, is based on information we believe to be reliable. However since particular conditions and methods of use involved in a particular product application are beyond our control, any such information is to be regarded as merely suggestive and should be verified by each user. Any suggestion made regarding the use of our products should not be construed as any authorization to infringe on patents, trademarks or similar rights of others.

Gellner Industrial, LLC, warrants that its products have been manufactured with due care, are free of defects in material or workmanship, and conform to the specifications stated in the data sheets applicable to each product or to specifications otherwise explicitly agreed upon in a writing which refers to this warranty. THIS WARRANTY IS IN LIEU OF ANY OTHER EXPRESS OR IMPLIED WARRANTIES, INCLUDING WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE. Gellner Industrial, LLC, Inc.'s liability under this warranty is limited to replacing, free of charge, any product that is found upon examination by Gellner Industrial, LLC, to be defective. Gellner Industrial, LLC, SPECIFICALLY DISCLAIMS ANY LIABILITY FOR CONSEQUENTIAL DAMAGES. It is strongly recommended that a prospective user of one of our products verify the suitability of that product for a given application before its use in production.